

IN THE CLAIMS

10. (Currently amended) A method of manufacturing a magnetic recording medium, comprising:

depositing a magnetic recording layer on a substrate,

depositing a caplayer on the magnetic recording layer and

annealing the caplayer *in situ* at a temperature of from about 150°C to about 550°C thereby manufacturing said magnetic recording medium.